

PCT/EP200 4 / 0 1 0 3 7 6

16 SEP 2004

REC'D 20 OCT 2004

WIPO

PCT

PA 1137005

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

February 27, 2004

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE UNDER 35 USC 111.


APPLICATION NUMBER: 60/532,411

FILING DATE: December 16, 2003

**PRIORITY
DOCUMENT**

**SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)**

**By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS**



P. Swain

P. SWAIN

Certifying Officer

BEST AVAILABLE COPY

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label N .

ER573872064US

INVENTOR(S)

Given Name (first and middle (if any))	Family Name or Surname	Residence (City and either State or Foreign Country)
Shahram	Mihan	Ludwigshafen, Germany
Wolfgang	Gsella	Köln, Germany
Peter	Kölle	Bad Dürkheim, Germany

☒ Additional inventors are being named on the 1 separately numbered sheets attached hereto

TITLE OF THE INVENTION (500 characters max)

SUSPENSION POLYMERIZATION WITH HIGH SOLIDS CONCENTRATIONS IN A LOOP REACTOR

Direct all correspondence to:

CORRESPONDENCE ADDRESS



Customer Number

34872

Type Customer Number here

OR



Firm or
Individual Name

William R. Reid

PATENT TRADEMARK OFFICE

Address

Basell USA Inc.

Address

912 Appleton Road

City

Elkton

State

MD

ZIP

21921

Country

US

Telephone

410-996-1783

Fax

410-996-1560

ENCLOSED APPLICATION PARTS (check all that apply)



Specification Number of Pages

10



CD(s), Number



Drawing(s) Number of Sheets



Other (specify)



Application Data Sheet. See 37 CFR 1.76

METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT



Applicant claims small entity status. See 37 CFR 1.27.



A check or money order is enclosed to cover the filing fees



The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number:

08-2336



Payment by credit card. Form PTO-2038 is attached.

FILING FEE
AMOUNT (\$)

\$160.00

The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.

☒ No.

☐ Yes, the name of the U.S. Government agency and the Government contract number are:

Respectfully submitted,

SIGNATURE

William R. Reid

TYPED or PRINTED NAME

William R. Reid

TELEPHONE

410-996-1783

Date

12/16/2003

REGISTRATION NO.

(if appropriate)

Docket Number.

47,894

LU 6133 (US)

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C. 20231.

BEST AVAILABLE COPY

PROVISIONAL APPLICATION COVER SHEET

Additional Page

PTO/SB/16 (02-01)
Approved for use through 10/31/2002. OMB 0651-0032
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Docket Number LU 6133 (US)

INVENTOR(S)/APPLICANT(S)		
Given Name (first and middle (if any))	Family or Surname	Residence (City and either State or Foreign Country)
Joachim	Wulff-Döring	Frankenthal, Germany

Number 2 of 2

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

BEST AVAILABLE COPY

EXPRESS MAILING CERTIFICATE

This certifies that the attached **Form PTO/SB/16** (in duplicate), **Specification (10 pages)** for the provisional application of **Shahram Mihan et al.** for **SUSPENSION POLYMERIZATION WITH HIGH SOLIDS CONCENTRATIONS IN A LOOP REACTOR** (our ref: **LU 6133 (US)**) is being mailed by "Express Mail Post Office to Addressee" service in an envelope addressed:

Mail Stop Provisional Patent Application
Commissioner for Patents
P. O. Box 1450
Alexandria, VA 22313-1450

and deposited on **December 16, 2003** as "Express Mail" in the United States Postal Service, the number of the "Express Mail" mailing label being **ER573872064US**.

Kyle Boulden

Typed Name of Person Mailing Paper or Fee


Signature of Person

SUSPENSION POLYMERIZATION WITH HIGH SOLIDS CONCENTRATIONS IN A LOOP REACTOR

The present invention relates to a process for polymerizing at least one olefinic monomer in a loop reactor at from 20 to 150°C, but below the melting point of the polymer to be formed, and a pressure of from 5 to 100 bar, where the polymer formed is present in a suspension in a liquid or supercritical suspension medium and this suspension is circulated by means of an impeller pump.

Suspension polymerization processes for polymerizing olefins have been known for a long time. A suspension polymerization in which the polymerization is carried out in a loop reactor has been found to be particularly useful for the polymerization of ethylene in particular, usually together with further comonomers. In such loop reactors, the polymerization mixture is pumped continuously through a cyclic reactor tube. The pumped circulation firstly achieves continual mixing of the reaction mixture, and also distributes the catalyst metered in and the feed monomers in the reaction mixture. Secondly, the pumped circulation prevents sedimentation of the suspended polymer. The removal of the heat of reaction via the reactor wall is also promoted by the pumped circulation.

The polymer is generally discharged from the loop reactor in a discontinuous fashion in sedimentation legs. These sedimentation legs are projections which branch off vertically from the lower part of the reactor tube and in which the polymer particles can settle. After sedimentation of the polymer has reached a particular point, a valve at the lower end of the sedimentation legs is opened briefly and the polymer which has settled is discharged discontinuously.

Since loop reactors have been used for production purposes for many years, numerous efforts have been made to improve the economics of these reactors and the polymerization processes carried out therein. An increase in the space-time yield of the process is particularly desirable. The space-time yield is, in particular, limited by removal of the heat of reaction via the reactor wall and by the polymer content of the reaction suspension. An increase in the proportion of solids in the reactor will, in particular, make discharge of the polymer more effective and increase the mean residence time of the polymer in the reactor.

US-A-6,239,235 describes a polymerization process in a loop reactor, in which an increase in the average proportion of solids in the reactor is achieved by means of a continuous

discharge system. This continuous discharge system was able to achieve an average proportion of solids in the reactor of 53% by weight, whereas the conventional discontinuous discharge achieved an average solids concentration of only 45% by weight. In accordance with conventional teachings, the document makes no reference to a varying reactor diameter; in contrast, disturbance-free flow is said to be achieved by means of gentle curves. Only in the region of the impeller pump does there seem to be, apparently for reasons of impeller construction, a short widening of the reaction tube diameter. The process described in this document, too, leaves something to be desired in respect of the solids concentration in the reactor. The document also confirms the prevailing view that it is generally not possible to achieve polymer solids concentrations of more than 37-40 percent by weight in suspension polymerization processes.

It is an object of the present invention to find a process for polymerizing olefinic monomers in a loop reactor, which process makes higher solids concentration in the reactor and higher space-time yields possible.

We have found that this object is achieved by the process described at the outset wherein the polymerization is carried out at an average solids concentration in the reactor of more than 53% by weight, based on the total mass of the contents of the reactor, in the case of continuous product discharge and at an average solids concentration in the reactor of more than 45% by weight, based on the total mass of the contents of the reactor, in the case of discontinuous product discharge.

In addition, we have found a process described at the outset wherein the polymerization is carried out at an average solids concentration in the reactor of more than 53% by weight, based on the total mass of the contents of the reactor, in the case of continuous product discharge and at an average solids concentration in the reactor of more than 45% by weight, based on the total mass of the contents of the reactor, in the case of discontinuous product discharge, and wherein the loop reactor used comprises a cyclic reactor tube whose diameter varies by at least 10%, based on the predominant reactor tube diameter, and in which there is at least one widening and narrowing in a region other than that of the impeller pump. It is also advantageous if the reactor tube additionally has a widening and narrowing in the region of the impeller pump.

The process of the present invention is suitable for polymerizing various olefinic monomers, in particular for polymerizing ethylene, propylene and 1-butene or mixtures of these

monomers. It is also possible to use additional monomers as comonomers, e.g. further α -olefins such as 1-pentene, 1-hexene, 1-octene or 1-decene.

Particular preference is given to a process in which ethylene is used as monomer and at least one α -olefin having from 3 to 8 carbon atoms, preferably 1-butene, 1-hexene or 1-octene, is used as comonomer. The amount of comonomer depends on the incorporation behavior of the particular catalyst in respect of the comonomer and on the desired density of the copolymer. The more comonomer incorporated into the polymer, the lower the density of the copolymer will be. A person skilled in the art can readily set the monomer:comonomer ratio on the basis of these considerations.

If the catalyst permits, vinylaromatic comonomers such as styrene or polar comonomers such as vinyl acetate, vinyl alcohols, acrylic acid or acrylic esters can also be polymerized. Cyclic monomers such as norbornene and dienes such as butadiene, 1,5-hexadiene or 1,7-octadiene are also possible as comonomers.

The polymerization process of the present invention can advantageously be carried out at from 20 to 150°C, preferably from 50 to 110°C, with an upper limit being imposed on the reaction temperature by the melting point of the polymer to be formed.

The reaction pressure is usually in the range from 5 to 100 bar, preferably from 10 to 80 bar. Low pressures are generally associated with low space-time yields, while higher pressures require an increased capital investment and lead to higher energy costs for compression. In general, a reaction pressure in the range from 20 to 50 bar represents a good compromise between apparatus cost and reaction yield. When supercritical suspension media such as supercritical propane are employed, a higher pressure above the critical pressure can be appropriate from a technical point of view.

Suitable suspension media for the process of the present invention are all media which are generally known for use in loop reactors. The suspension medium should be inert and be liquid or supercritical under the reaction conditions and should have a boiling point which differs significantly from those of the monomers and comonomers used in order to make it possible to recover the starting materials from the product mixture by distillation. Examples of customary suspension media are isobutane, butane, propane, isopentane, pentane and hexane.

An important feature of the process of the present invention is that it allows polymerization at high ethylene concentrations. High proportions of solids in the reactor, in the

present context also referred to simply as "reactor density", result in the proportion of the suspension medium in the reactor being correspondingly lower. In general, the smaller volume of the suspension medium results in the amount of ethylene in the reactor also being lower, which leads to reduced polymer formation. In contrast, the process of the present invention
 5 makes it possible to increase the ethylene concentration in the suspension medium and thus achieve higher polymer formation and a higher polymerization rate even at high reactor densities.

In a preferred embodiment of the process of the present invention, the polymerization is therefore carried out at an ethylene concentration of at least 10 mol%, based on the suspension
 10 medium.

Thus, ethylene concentrations of 15 mol% and even 17 mol%, based on the suspension medium, were achieved in the process of the present invention.

In this context, the term "suspension medium" refers not simply to the suspension medium used, e.g. isobutane, but to the mixture of this suspension medium with the monomers
 15 dissolved therein. The ethylene concentration can be determined easily by gas-chromatographic analysis of the suspension medium.

As mentioned at the outset, the technology of loop reactors has been known for a long time. In general, these reactors consist essentially of a cyclic reactor tube having one or more ascending and one or more descending segments which are surrounded by cooling jackets for
 20 removing the heat of reaction and also horizontal tube sections which connect the vertical segments. The lower tube section usually accommodates the impeller pump, the feed facilities for catalyst and monomer and the discharge device, i.e. generally the sedimentation legs. However, the reactor can also have more than two vertical tube sections, so that a meandering arrangement is obtained.

25 The present invention makes it possible to carry out a suspension polymerization process in a loop reactor at solids concentrations of more than 53% by weight, based on the total mass of the contents of the reactor, and thus increase the production capacity of the loop reactor. These high solids concentrations can be achieved by various means.

In one embodiment of the present invention, the high solids concentration is achieved by
 30 the diameter of the cyclic reactor tube being varied by more than 10%, based on the predominant reactor tube diameter. A widening of the reactor tube in the region of the impeller pump

necessitated by the construction should not be taken into consideration here, since such a widening serves primarily to accommodate the impeller in the reaction tube and highly turbulent flow prevails in this region in any case. Rather, the invention is based inter alia on the observation that, contrary to prevailing opinion, deliberate nonuniform flow of the polymerization mixture in the region of the reaction tube even outside the region of the impeller makes it possible to increase the solids concentration in the reactor. This effect appears, without wishing to be tied to this hypothesis, to be based on more effective mixing of the heterogeneous reaction mixture. In particular, the monomer fed in, e.g. ethylene, is apparently dispersed more quickly in the reaction mixture, is dissolved more quickly in the suspension medium and is available to a greater degree for the polymerization. The removal of the heat of reaction also appears to be aided, since the disturbance of the flow increases motion perpendicular to the flow direction, i.e. in the direction of the cooled reactor wall, which occurs to only a very limited extent in the case of uniform plug flow.

To be able to influence the flow conditions in this desired way, the reaction tube diameter should be varied to a particular degree. The diameter of the tube should vary by at least 10%, based on the predominant diameter of the reactor tube. For the present purposes, the predominant diameter of the reactor tube is the tube diameter which is constant over the longest stretch of the reactor tube. The tube diameter should preferably vary by at least 20%, even better by at least 30% and very particularly preferably by at least 50%.

The conical widening of the reactor tube diameter in the flow direction should have a cone angle of about $0.5-10^\circ$, preferably $0.5-1.5^\circ$, and the cone angle at the narrowing of the tube diameter down to the predominant tube diameter should be about $0.5-10^\circ$, preferably $1-3^\circ$.

The length of the sections having a widened tube diameter is preferably from 2 to 30 times the predominant tube diameter, particularly preferably from 5 to 15 times this tube diameter.

In a preferred embodiment of the process of the present invention, there is also an additional widening and narrowing of the reaction tube in the region of the impeller pump. As mentioned above, such widenings necessitated by the construction are already known. The effect of these widenings in accordance with the present invention can, however, be increased by making the widening greater and possibly also extending it over a longer section of the tube than is required by the construction.

The effect of the present invention in terms of enabling the solids concentration in the reactor to be increased appears to be based, inter alia, on better mixing of the monomer in the reaction mixture. It has been found that this inventive effect can be increased by feeding the monomer, i.e. for example ethylene, in at various points along the reaction tube. An advantageous embodiment of the process of the present invention therefore comprises feeding at least one olefinic monomer in at at least 2 points along the reactor tube. It has been found to be advantageous for the monomer to be fed in at, for example, 3 or 4 points along the reactor tube. These feed points can be provided uniformly along the reactor tube, and it is advantageous for the feed points to be located in each case upstream of the widenings of the tube, but not in the region of the last vertical segment before the product discharge region.

It is known from US-A-6,239,235 that a continuous discharge system can also be useful for increasing the solids concentration in the reactor. This measure can be combined with the process of the present invention. Accordingly, the present invention also provides a process as described above in which the polymer formed is discharged continuously from the reactor.

The high solids concentration in the reactor which is sought according to the present invention can, as indicated above, be achieved by the abovementioned means. Particular preference is given to a process in which the polymerization is carried out at an average solids concentration in the reactor of more than 53% by weight, based on the total mass of the contents of the reactor. This solids concentration is preferably above 55% by weight, more preferably above 58% by weight and particularly preferably above 60% by weight. As shown in the examples, solids concentrations of more than 62% by weight can be achieved. For the present purposes, the average solids concentration is then the solids concentration in the reaction tube. Even higher solids concentrations can be observed in the discharge system, whether continuous or discontinuous, due to sedimentation.

The high solids concentrations can be achieved by the measures provided by the present invention even without continuous discharge of the polymer product. One variant of the process of the present invention therefore comprises discharging the polymer formed from the reactor in a discontinuous fashion and carrying out the polymerization at an average solids concentration in the reactor of more than 45% by weight, based on the total mass of the contents of the reactor.

Under these conditions, the solids concentration in the reactor is preferably above 50% by weight, particularly preferably above 55% by weight.

The process of the present invention can be operated as a single-stage process, but can also be carried out as a multistage cascade process by combining it with further polymerization reactors. One embodiment of the process of the present invention is therefore a process for polymerizing at least one olefinic monomer in a loop reactor, wherein the polymerization in this loop reactor is preceded or followed by at least one further polymerization step in a loop reactor or a gas-phase reactor. Such cascade processes, albeit without the specific features of the present invention, are described, for example, in EP-A-517 868 and US-A-6 355 741.

Apart from the above-described disturbance of the suspension flow in the reaction tube, a high reactor density can also be achieved by other measures, for example by selection of a particularly suitable catalyst.

Catalysts suitable for use in the process of the present invention are in principle all catalysts which are also used otherwise in loop reactors, i.e., for example, chromium catalysts of the Phillips type, Ziegler catalysts, Ziegler-Natta catalysts or single-site catalysts such as metallocene catalysts. Phillips catalysts have become particularly widespread in loop reactors, and can also be used particularly advantageously in the process of the present invention. Among these catalysts, particular preference is given to those described in the patent applications WO-01/18069, WO-01/17675, WO-01/17676 and WO-01/90204. It has been determined that, surprisingly, that these catalysts make it possible to achieve very high solids concentrations in the reactor, even without the reactor tube of the loop reactor having a varying tube diameter.

The examples which follow illustrate the process of the invention:

Examples

The preparation of the catalyst up to the activation step was carried out by the method described in WO-01/90204. Activation was then carried out at 520°C in the presence of air in a fluidized-bed activator. Fluoride doping was carried out by use of a mixture of the catalyst precursor with 2.5% by weight of ammonium hexafluorosilicate (resulted in a fluoride content of about 1% by weight, based on the total mass of the catalyst) in the activation. For activation, this mixture was heated to 350°C over a period of 1 hour, maintained at this temperature for 1 hour, subsequently heated to the desired activation temperature of 520°C, maintained at this temperature for 2 hours and subsequently cooled, with cooling below 350°C being carried out under N₂.

Polymerization:

Ethylene was copolymerized with 1-hexene at 104°C and a pressure of 39 bar using the above-described catalyst in a loop reactor having a reactor volume of 0.18 m³. Ethylene was fed into the reactor at two points, one shortly before the impeller. Isobutane was used as suspension medium. The isobutane was fed into the reactor at 6 points, including in the region of the impeller pump shaft and the place where the catalyst was introduced. The impeller pump was operated at 1700-1900 revolutions per minute. The product was discharged discontinuously via customary sedimentation legs. Polymerizations were carried out at slightly different ethylene/isobutane ratios, but the resulting product always had a density of about 0.949 g/ccm and a high-load melt index (21.6/190) of about 2.0.

Experiment No.	1	2	3	4	5	6	7
Ethene addition (kg/h)	33	35	34	33	33	33	33
Isobutane addition (kg/h)	34	31	28	24	19	13	10
Ethene/isobutane	0.97	1.12	1.21	1.38	1.74	2.54	3.24
Ethene fraction in suspension medium (mol%)	9.6	11.4	12.5	14.7	16.1	16.0	15.7
Solids concentration in reactor (% by weight)	48.0	55.2	58.8	61.2	64.8	66.9	68.8
Productivity (g polymer/g catalyst)	4300	6900	7634	7752	9174	9259	10989
Powder density (kg/m ³)	480	500	506	513	515	522	516

We claim:

1. A process for polymerizing at least one olefinic monomer in a loop reactor at from 20 to 150°C, but below the melting point of the polymer to be formed, and a pressure of from 5 to 100 bar, where the polymer formed is present in a suspension in a liquid or supercritical suspension medium and this suspension is circulated by means of an impeller pump, wherein the polymerization is carried out at an average solids concentration in the reactor of more than 53% by weight, based on the total mass of the contents of the reactor, in the case of continuous product discharge and at an average solids concentration in the reactor of more than 45% by weight, based on the total mass of the contents of the reactor, in the case of discontinuous product discharge.
2. A polymerization process as claimed in claim 1, wherein the loop reactor comprises a cyclic reactor tube whose diameter varies by at least 10%, based on the predominant reactor tube diameter, and in which there is at least one widening and narrowing in a region other than that of the impeller pump.
3. A process as claimed in claim 1 or 2, wherein there is an additional widening and narrowing of the reactor tube in the region of the impeller pump.
4. A process as claimed in any of the preceding claims, wherein ethylene is used as monomer and at least one α -olefin having from 3 to 8 carbon atoms is used as comonomer.
5. A process as claimed in any of the preceding claims, wherein at least one olefinic monomer is fed in at at least 2 points along the reactor tube.
6. A process as claimed in any of the preceding claims, wherein the polymer formed is discharged continuously from the reactor.
7. A process as claimed in any of the preceding claims, wherein the polymerization is carried out at an ethylene concentration of at least 10 mol%, based on the suspension medium.
8. A process for polymerizing at least one olefinic monomer in a loop reactor as claimed in any of the preceding claims, wherein the polymerization in this loop reactor is preceded or followed by at least one further polymerization step in a loop reactor or a gas-phase reactor.

Abstract

Process for polymerizing at least one olefinic monomer in a loop reactor at from 20 to 150°C, but below the melting point of the polymer to be formed, and a pressure of from 5 to 100 bar, where the polymer formed is present in a suspension in a liquid or supercritical suspension medium and this suspension is circulated by means of an impeller pump, wherein the polymerization is carried out at an average solids concentration in the reactor of more than 53% by weight, based on the total mass of the contents of the reactor, in the case of continuous product discharge and at an average solids concentration in the reactor of more than 45% by weight, based on the total mass of the contents of the reactor, in the case of discontinuous product discharge.